



Performance	
Coefficient of thermal conductivity $\boldsymbol{\lambda}$	≤ 0.18
Density	= 0.57 ± 0.02
Soluble silica (hydraulicity)	≤ 7.2%
CO ₂ content	≤ 13%
Additives (organic colloids and surfactants)	< 0.8%
Water retention	≥ 73%
Particle size distribution	≤ 90 μm
Pulling/bending	≥ 0.3 N/mm²
Compression	≥ 1 N/mm²

Tradical® PF 80 includes

Tradical® "Masonry and Rendering with lime"

- -Tradical® PF 55
- -Tradical® Maçonner
- -Tradical® Bâtir
- -Tradical® PF 80 M
- -Tradical® PF 80 Teinté
- -Tradical® PZ
- -Tradical® Premium Naturel



Lhoist Southern Europe

ZAC de Valentin - BP 3011 25045 BESANÇON cedex Tél. + 33 [0]3 81 47 40 10 Fax + 33 [0]3 81 47 40 19 contact@bcb-tradical.com www.bcb-tradical.com

Tradical® PF 80

Aerial lime binder pre-formulated for rendering and pointing Complies with the French Building Code (DTU 26.1 and 20.1)

Definitions and areas of use

→ Tradical® PF 80 is a binder based on aerial lime (85%), hydraulic binders (15%) and mineral fillers, suitable for mixing with aggregates (sand) and water to use in soft stone masonry and to form a traditional base coat, brown coat and single-mass render and for repointing on old substrates in compliance with the French Building Code (DTU 20.1, sections 2.2 and 4.21, DTU 26.1, section 11).

→ Tradical® PF 80 has water repellant properties.

\rightarrow STORAGE

Store in its original bag (20 kg) in a sheltered place. Tradical® PF 80 binder can be stored for 12 months.

→ DESIGN OF STRUCTURES AND APPLICATION

Refer to the French Building Code in force for the type of structure.

- Masonry: DTU 20.1, sections 2.2 and 4.21
- Render/Repointing: DTU 26.1, section 11

\rightarrow SUBSTRATES

For renders, moisten the substrate the day before until the saturation point is reached. Re-moisten if required and leave to dry.

Do not apply to frozen, thawing, overheated or streaming substrates.

The substrates must be suitable as per the specifications.

→ PREPARATION

Mix the sand according to the proportions listed in the relevant technical guide, without adding any hydraulic binders. Then mix to form the desired consistency by adding clean water.

Mix for 3 to 5 minutes in a concrete mixer.

→ APPLICATION

Apply at a temperature of between +5 °C and +35 °C, away from sunlight, strong winds, and heavy rainfall.

Mechanical application or by pneumatic projection:

- → Refer to the material manufacturer for the amount of sand to use.
- → Apply in the same manner as a traditional mortar.

→ MIX PROPORTIONS

The mix proportion of binder in relation to sand depends on:

a) the type of structure rendered, and

b) the sand used (particle size distribution, type, and moisture content)

As a rule, the measure of binder is:

- \rightarrow 200 to 300 kg per m³ of sand (moisture of less than 5%).
- \rightarrow or by volume: 1 part binder to 2 to 3.5 parts sand

Can be used as a thin mix or a pure paste

→ MISCELLANEOUS

Testing

Each production batch is lab-tested. A sample is stored and the corresponding reference is noted on each baq.

Guarantee

Within the scope of the company's civil liability insurance. Manufacturer's civil liability, SMABTP contract: ALPHA-BAT Fabricants no. 512806 E.



For further information visit our website www.ozhemp.com.au
Email: info@ozhemp.com.au
Tel: 61 8 6424 8262 Fax: 61 8 6424 8782